



Application Note AN-PAN-1019

Online analysis of acids and iron in pickling baths

In the galvanic industry, pickling baths are utilized to clean and remove most oxides from various steel surfaces, as well as to passivate the surface to prevent corrosion.

It is crucial to maintain specific limits for the $\text{Fe}^{2+}/\text{Fe}^{3+}$ and free acid/total acid ratios to ensure the chemical bath remains in optimal working condition. The proper composition of the baths directly affects the quality of the final products. By maintaining these parameters

within optimal ranges, the quality of the resulting products is improved, and production costs are lowered due to decreased reagent consumption.

This Process Application Note presents a method to regularly monitor the acid and iron composition in pickling baths online to ensure an even cleaning process by using a process analyzer from Metrohm Process Analytics.

INTRODUCTION

Countless products begin with steel, which is one of the most essential raw materials.

Hot-dip galvanizing (**Figure 1**) is a process that involves coating steel (or iron) with a layer of zinc to protect it from corrosion [1]. An extremely important part of steel production is the **pickling process**, in which impurities such as mill scale produced during high-temperature rolling are removed and the surface prepared for subsequent process steps. At the same time, interfering annealing colors are removed while the surface is passivated by the formation of a protective layer to protect against further corrosion.

The pickling baths used are made up of diluted acids and can vary in composition depending on the grade of steel being treated. In most cases, hydrochloric or sulfuric acid (HCl , H_2SO_4) are

used, or mixtures of acids such as HNO_3/HF or $\text{H}_2\text{SO}_4/\text{H}_3\text{PO}_4/\text{HF}$. While pickling removes impurities, the acids used also attack the steel surface and partially dissolve it. This over-pickling of the base steel can result in the **metal pitting** which leads to an undesirable rough, blistered coating in the following galvanizing steps, and also causes *excessive consumption* of the pickling acid. Dissolved iron in the form of iron oxides present in the metal oxide scale affects the pickling rate of steel as iron concentrations increase. Therefore, it is important that process-relevant parameters such as **bath composition** are controlled and maintained as accurately as possible to reduce the overconsumption of pickling chemicals while keeping the quality of the product constant.

GALVANIZING PROCESS




Figure 1. Illustration of the multi-step hot-dip galvanizing process. The pickling bath is shown in light blue.

Pickling is a highly corrosive process, and if the bath is not monitored carefully, it can lead to issues in the resulting product. Continuous online monitoring of **free and total acids** and **iron content** satisfies this requirement and as a result, pickling baths can be used more economically and ecologically. Thus, operating

and chemical disposal costs are considerably reduced.

Metrohm Process Analytics offers a multi-parameter process analyzer that is suitable for the simultaneous analysis of $\text{Fe}^{2+}/\text{Fe}^{3+}$ and free acid/total acid ratio over a wide concentration range—the **2060 TI Process Analyzer** (Figure 2).



Figure 2. 2060 TI Process Analyzer for the online analysis of critical quality parameters in pickling baths using the method of titration.

APPLICATION

Total acids, individual acids, and iron (i.e., HCl, H_2SO_4 , HNO_3 , HF, Fe_2^+ , and Fe^{3+}) were analyzed using accurate titration methods. Performance monitoring of pickling baths is possible with the

use of Metrohm process analyzers, either the 2026 HD Titrolyzer or the 2060 TI Process Analyzer, depending on whether single- or multi-parameter measurements are required.

Table 1. Parameters and their concentration ranges in pickling baths.

| Parameters | Concentration [g/L] |
|--------------------------------|---------------------|
| HCl | 15–250 |
| Fe ²⁺ | 10–200 |
| Fe ³⁺ | 1–20 |
| HNO ₃ | 10–250 |
| HF | 0–100 |
| H ₂ SO ₄ | 0–300 |

REMARKS

A settler (Figure 3) can be used as a robust preconditioning system to remove solids and particles from the liquid sample prior to the analysis.




Figure 3. Settler unit for removal of particles.

CONCLUSION

During steel production, the pickling process prepares the steel surface for subsequent finishing steps. These pickling baths contain combinations of HCl, H₂SO₄, HNO₃, HF, H₃PO₄, Fe²⁺, and Fe³⁺. For reproducible surface treatment, the bath composition must be continuously monitored. This is best done online

with titration by using a rugged Metrohm process analyzer such as the 2060 TI Process Analyzer. By supplying real-time information to the industrial control system (such as DCS or PLC) with an online process analyzer, downtimes are reduced, bath composition is optimized, and costly company assets are safeguarded.

REFERENCES

1. What is the HDG Process?. American Galvanizers Association.
<https://galvanizeit.org/hot-dip-galvanizing/hdg-process> (accessed 2023-05-08).

RELATED APPLICATION NOTES

[AN-PAN-1006](#) Determination of zinc, sulfuric acid and iron

[AN-PAN-1012](#) Online analysis of nickel ion & hypophosphite content

[AN-PAN-1018](#) Determination of acids, bases and aluminum: galvanic industry – metal surface treatment

OTHER RELATED DOCUMENTS

[WP-076](#) Process analyzers as proactive solutions

[for online corrosion monitoring](#)

BENEFITS FOR ONLINE PROCESS ANALYSIS

- **Enhanced** reproducibility, production rates, and profitability (less waste).
- **Fully automated diagnostics** – automatic alarms for when samples are out of specified concentration parameters.
- **Efficient steel pickling** at a high level of quality by constantly monitoring the processing baths.
- **Avoid unnecessary costs** by reducing the amount of time required to achieve the desired pickling results.



CONTACT

Metrohm AG
Ionenstrasse
9100 Herisau

info@metrohm.com

CONFIGURATION



2060 Process Analyzer

2060 Process Analyzer 是在湿化学分析,用于无数用。此程分析提供了一个新的模化概念,由一个称«主机»的中心平台成。

主机由部分成。上部包含触摸屏和工算机。下部含有柔性取部,其中放有用于分析的硬件。如果主取部容量不足以分析挑,那主机可以展多四个外的取部机,以保有足的空来具挑性的用。附加机的配置方式使每个取部机可以与具有集成(非接触式)液位的合使用,以增加分析的正常行。

2060 Process Analyzer 提供不同的湿化学技:滴定法、舍滴定法、光度定、直接量和准添加入法。

足所有目要求(或足的所有需求),可提供品理系,以保分析解决方案可靠。我可以提供任何品理系,如冷却或加、和脱气、等。